FICHE TECHNIQUE

No. 538

REVÊTEMENT POUR ACIER INOXYDABLE S316

Une formulation spéciale contenant du pigment d'acier inoxydable 316L pour fournir une résistance maximale à la corrosion et une protection contre les intempéries, la lumière du soleil, l'huile et l'eau. Finition satinée une fois sec. Recommandé comme couche de finition, ce produit n'est pas un apprêt. L'utilisation d'un apprêt est toujours bénéfique pour améliorer l'adhérence et la durabilité. Sèche rapidement et ne jaunit pas.

EMBALLAGE :

Code UPC	777954711695
Boîtes par caisse	6
Poids par caisse	7 lbs.
Poids du produit	340 gr
Classification expédition	Biens de consommation,ORM-D, UN 1950
Classe de danger	2.1

PROPRIÉTÉS :

Couverture	Jusqu'à 15 pieds carrés
Nettoyage	Peinture ou diluant à peinture
Inflammabilité	Extrêmement inflammable
Point d'éclair	-4 F°
Gravité spécifique	0,79
Contenu solide	17%
Valeur MIR	1,16, ne peut dépasser 1,25
Contenu HAPs	33%
Température de stockage	40-100 F°
Température d'application	50-90 F°
Résistance à l'essence	Non
Résistance à la chaleur	250 F°
Système de résine	Laque acrylique
Durée de conservation	Garantie pour 2 ans

TEMPS DE SÉCHAGE*:

Au toucher	5 minutes
Pour deuxieme couche	10 minutes

* À 72F°, 50% d'humidité, 1,5 mil d'épaisseur
** Le temps de durcissement / recouvrement est prolongé avec plusieurs couches et des couches excessivement épaisses

FINI*:

Faible Lustre
*mesuré sur un brillancemètre à 60 degrés

UTILISATIONS SUGGÉRÉES

- Protection du métal
- Structure de métal peinte
- Retouches de soudure

PR DISTRIBUTION

6500, rue Zéphirin-Paquet,
Parc industriel Armand Viau
Québec (Québec) Canada G2C 0M3

1 800 463-5259
www.prdistribution.ca

TECHNICAL SHEET

No. 538

S316 - STAINLESS STEEL COATING

A special formulation containing 316L stainless steel pigment to provide maximum corrosion resistance and protection against weather, sunlight, oil, and water. Dries to a satin finish. Recommended as a topcoat, not a primer. Use of a primer is always beneficial to enhance adhesion and overall durability. Dries quickly and is non-yellowing.

PACKAGING:

UPC Code	777954711695
Cans per case	6
Shipping weight per case	7 lbs.
Product weight	(340 grams)
Shipping Classification	Consumer Commodity, ORM-D, UN 1950
Hazard Class	2.1

PROPERTIES:

Coverage	Up to 15 square feet
Cleanup	Paint or lacquer thinner
Flammability	Extremely Flammable
Flash poin	-4 F°
Specific Gravity	0.79
Solids Content	17%
MIR value	1.16, cannot exceed 1.25
HAPs content	33%
Storage Temperature	40-100 F°
Application Temperature	50-90 F°
Gasoline Resistance	No
Heat Resistance	250 F°
Resin System	Acrylic lacquer
Shelf life	Guaranteed for 2 years

DRY TIME*:

To touch	5 minutes
To topcoat	10 minutes

* At 72F°, 50% humidity,1.5 mil thickness
Curing/Recoat time is extended with multiple coats and excessively thick coats

GLOSS*: Faible Lustre

*As measured on a 60 degree gloss meter

SUGGESTED USES:

- Protect metal
- Touch up appliances
- Paint metal structures
- Touch up weld

PR DISTRIBUTION

6500, rue Zéphirin-Paquet,
Parc industriel Armand Viau
Québec (Québec) Canada G2C 0M3

1 800 463-5259
www.prdistribution.ca